

EXALITE 392A

Synonyms: 7,7'-Bis(1,1-dimethylpropyl)-9,9,9',9'-tetraethyl-2,2'-bi-9*H*-fluorene
2,2'-bi-9*H*-fluorene, 7,7'-bis(1,1-dimethylpropyl)-9,9,9',9'-tetraethyl-

Catalog No.: 03921


CAS No.: 173406-98-9

MW: 582.90

Chemical Formula: C₄₄H₅₄

Appearance: White Crystalline solid

Structure:



Lasing Wavelength


Max. (nm)	Range (nm)	Pump Source (nm)	Solvent	Concentration (molar)	Abs λ-max	FI λ-max
--------------	---------------	---------------------	---------	--------------------------	--------------	-------------

The Exalite dyes (Exalite 392A, Exalite 404, Exalite 411, Exalite 417 and Exalite 428) all have excellent operating lifetimes. The preferred solvent is p-Dioxane. Most of these dyes have very high absorption coefficients at 355nm, making them excellent candidates for pumping with the third harmonic of the Nd:YAG laser as well as under XeCl(308nm) pumping.

392	373-397	XeCl(308) ^{177b}	p-Dioxane	4.2 x 10 ⁻⁴	331 ^c	368 ^c
389	382-396	Nd:YAG(355) ¹¹⁰	p-Dioxane	~6.5 x 10 ⁻⁵		385
389	383-398 407(sh)	Nd:YAG(355) ⁵⁷	p-Dioxane	2.8 x 10 ⁻⁴ (osc), 0.8 x 10 ⁻⁴ (amp)		

c = cyclohexane

Exalite 392A in Methanol



The information presented above is believed to be accurate but is not a specification. The customer is fully responsible for determining the suitability of this product for use in their application. Exciton, Inc. does not represent that the information is sufficient or complete for any specific application.

REFERENCES:

57. Quanta-Ray, Note: Quanta-Ray is now incorporated as a part of Spectra-Physics, 1250 W. Middlefield Road, Mountain View, CA 94039
110. Lumonics Inc., 105 Schneider Road, Kanata, (Ottawa), Ontario, Canada K2K 1Y3
177. Exciton and Associates, unpublished data, 1987-1989;
 - a. Characterization of New Excimer Pumped UV Laser Dyes I. p-Terphenyls, D.J. Schneider, D.A. Landis, P.A. Fleitz, C.J. Seliskar, J.M. Kauffman and R.N. Steppel, *Laser Chem.*, 11, 49 (1991);
 - b. Characterization of New Excimer Pumped UV Laser Dyes 2. p-Quaterphenyls, P.A. Fleitz, C.J. Seliskar, R.N. Steppel, J.M. Kauffman, C.J. Kelley and A. Ghiorghis, *Laser Chem.*, 11, 99 (1991);
 - c. Characterization of New Excimer Pumped UV Laser Dyes 3. p-Quinqui-, Sexi-, Octi- and Deciphenyls, C.J. Seliskar, D.A. Landis, J.M. Kauffman, M.A. Aziz, R.N. Steppel, C.J. Kelley, Y. Qin and A. Ghiorghis, *Laser Chem.*, 13(1), 19 (1993)