



ABS 697: Visible Absorber

Properties

Composition Proprietary metal complex¹

Peak Wavelength 694 ± 2 nm (methylene chloride), 697 ± 2 nm (polycarbonate)


Strength > 216 L/gm-cm

Appearance Dark blue crystalline solid

Solubility Low solubility in organic solvents, insoluble in water

Melting Point > 200 °C Solar Stability Excellent

Spectrum



1. This product is offered by Exciton, Inc. under non-analysis and may be available for licensing for specific applications that require selective absorption and high temperature stability. Please contact Exciton for licensing or additional technical information.

The information presented above is believed to be accurate but is not a specification. The customer is fully responsible for determining the suitability of this product for use in their application. Exciton, Inc. does not represent that the information is sufficient or complete for any specific application.