




www.exciton.luxottica.com

IRA 945B: Infrared Absorber

Properties

Composition	Proprietary Organic Salt ¹
Peak Wavelength	936 ± 1 nm (methylene chloride)
Strength	> 80 L/gm-cm (methylene chloride)
Appearance	Dark green solid
Solubility	15.3 gm/L (chloroform), 0.32 gm/L (toluene),
	6.9 gm/L (cyclohexanone), 0.3 gm/L (ethanol)
Melting Point	> 180 °C
Solar Stability	Not determined

Spectrum (methylene chloride)



This product is offered by Exciton, Inc. under non-analysis and may be available for licensing for specific applications that require selective absorption and high temperature stability. Please contact Exciton for licensing or additional technical information.

The information presented above is believed to be accurate but is not a specification. The customer is fully responsible for determining the suitability of this product for use in their application. Exciton, Inc. does not represent that the information is sufficient or complete for any specific application.